

NF372-TB Soldering Flux

Zero-Halogen, High-Reliability, No-Clean Liquid Flux

Product Description

Kester NF372-TB Soldering Flux is a zero-halogen, no-clean, low solids liquid flux designed for use in wave and hand soldering processes. It can be used with both leaded and lead-free alloys. A key feature is its wide processing window for thin boards and thick boards that require short or long dwell times and high preheat temperatures. Sustained activity within the flux allows for good barrel fill in challenging applications, such as reflowed copper OSP boards or with difficult to solder components. NF372-TB residues are minimal, clear and non-tacky for improved cosmetics. For a list of compatible products, visit the Kester website or contact Kester Technical Support.

Performance Characteristics:

- Zero-Halogen (none intentionally added)
- Provides good solderability under air atmosphere
- Classified ROL0 per IPC J-STD-004B
- Non-corrosive, non-conductive and non-tacky residues
- Pass SIR in raw state (unheated boards dried at 25 °C/50%RH for 24 hours before test)
- Compliant to GR-78-CORE (Telcordia/Bellcore)
- Ability to provide desired hole-fill with preheat temperatures up to 140 °C max
- Safe for rework (available in flux-pens)

Advantages:

- Wide process preheat window of 75 to 140 °C that accommodates both thin and thick board applications
- High reliability flux that passes both IPC SIR 85/85 and SIR 40/90 and Bono Test for both leaded and lead-free alloys
- Pallet process friendly
- Extends pallet life and does not attack pallet materials
- The seepage of the flux between pallets and PCB is safer and does not cause reliability issues in condensing or high humidity environment

RoHS Compliance

This product meets the requirements of the Restriction of Hazardous Substances (RoHS) Directive. Additional RoHS information is located at <https://www.kester.com/downloads/environmental>.

Physical Properties

Acid Number (typical): 16.6 mgKOH/gm

Specific Gravity @ 25 °C: 0.793 (typical)

Solids Content (theoretical): 3.90 %

Reliability Properties

Copper Mirror: Low

Tested to J-STD-004B, IPC-TM-650, Method 2.3.32

Copper Corrosion: Low

Tested to J-STD-004B, IPC-TM-650, Method 2.6.15

Electrochemical Migration (ECM): Pass

Tested to J-STD-004B, IPC-TM-650, Method 2.6.14.1

Test Conditions: 65 °C, 90% RH, 25 days, 100V

Surface Insulation Resistance (SIR): Pass; [All Readings > $1.0 \times 10^8 \Omega$]

Tested to J-STD-004B, IPC-TM-650, Method 2.6.3.7

Test Conditions: 40 °C, 90% RH, 7 days, 12.5V

Surface Insulation Resistance (SIR): Pass

Tested to J-STD-004A, IPC-TM-650, Method 2.6.3.3

Test Conditions: 85 °C, 85% RH, 7 days, 100V

Surface Insulation Resistance, Bellcore, IPC: Pass; [All Readings > $2.0 \times 10^{10} \Omega$]

GR-78 13.1.3

Test Conditions: 35 °C, 85% RH, 4 days, 100V

Halogen Content: None detected

Tested to J-STD-004B, IPC-TM-650, Method 2.3.28.1

Bono Corrosion Test: Pass; [Fc = 0.5%]

Test Conditions: 85 °C, 85% RH, 15 days, 12V

Process Considerations / Recommendations

NF372-TB is designed for spray fluxing. This flux is not designed for foam applications. The information below is a guideline. It is advisable to note that the optimum setting for a given assembly may vary and this is dependent on the circuit board design, board thickness, components used, and equipment used. A design of experiment is recommended to be done to optimize the soldering process.

Process Parameters	Recommendation
Flux deposition	600 to 1400 $\mu\text{g}/\text{in}^2$ of solids (93 to 217 $\mu\text{g}/\text{cm}^2$) of solids
Top side board temperature (bottom preheaters only)	75 to 120 °C ^{2,3}
Top side board temperature (bottom and top preheaters) ¹	95 to 140 °C ^{2,3}
Bottom side board temperature	0 to 32 °C vs top side board temperature ³
Recommended preheat profile	Straight ramp to top side board temperature
Conveyor speed	0.5 to 1.2 m/min (1.6 to 3.9 ft/min)
Solder contact time	3 to 7 seconds
Solder bath temperature	260 to 270 °C (500 to 518 °F) for SnCu or SAC alloy 245 to 260 °C (473 to 500 °F) for Sn63Pb37 alloy

¹ When board is heated from top and bottom, there will be a smaller delta temperature between top and bottom of the board and minimizing the risk of sublimation. The top heater should be set between 10 to 20 °C higher the setting bottom heater under it. This will tend to draw the solder up to the top of the board. Caution: Using top and bottom preheaters simultaneously does not ensure the center of the board reach proper temperature for soldering.

² Caution: Lower top side board temperature is acceptable only in low thermal areas of an assembly with proper lead/hole clearance.

³ Board temperature should not exceed 140 °C.

Flux Control

NF372-TB is designed to be sprayed. Incoming solderability inspection of circuit boards and components is advisable as a part of process control to maintain consistent soldering results.

Cleaning

NF372-TB residues are non-conductive, non-corrosive and do not require removal in most applications. If residue removal is required, it can be removed using commercially available flux residue cleaner. Contact Kester Technical Support for additional assistance.

Compatibility

NF372-TB is compatible with Humiseal conformal coating UV40, 1B31 and UB500.

Recycling Services

We provide safe and efficient recycling services to help companies meet their environmental and legislative requirements and at the same time, maximize the value of their waste streams.

Our service collects solder dross, solder scrap, and various forms of solder paste waste. Please contact your local sales representative for recycling capabilities in your area or [link here](#).



Storage, Handling and Shelf Life

NF372-TB is flammable. Store away from sources of ignition. Shelf life is 2 years from the date of manufacture when handled properly and held at 10 to 25 °C (50 to 77 °F).

Health and Safety

This product, during handling or use, may be hazardous to your health or the environment. Read the Safety Data Sheet and warning label before using this product. Safety Data Sheets are available at this [link](#).

Contact Information

To confirm this document is the most recent version, please contact Assembly@MacDermidAlpha.com

<p>North America 109 Corporate Blvd. South Plainfield, NJ 07080, USA 1.800.253.7837</p>	<p>Europe Unit 2, Genesis Business Park Albert Drive Woking, Surrey, GU21 5RW, UK 44.01483.758400</p>	<p>Asia Pacific 8/F., Paul Y. Centre 51 Hung To Road Kwun Tong, Kowloon, Hong Kong 852.3190.3100</p>
--	--	---

Also read carefully warning and safety information on the Safety Data Sheet. This data sheet contains technical information required for safe and economical operation of this product. READ IT THOROUGHLY PRIOR TO PRODUCT USE. Emergency safety directory assistance: US 1 202 464 2554, Europe + 44 1235 239 670, Asia + 65 3158 1074, Brazil 0800 707 7022 and 0800 172 020, Mexico 01800 002 1400 and (55) 5559 1588

DISCLAIMER: All statements, technical information and recommendations contained herein are based on tests we believe to be reliable, but the accuracy or completeness thereof is not guaranteed. No statement or recommendation shall constitute a representation unless set forth in an agreement signed by officers of seller and manufacturer. NO WARRANTY OF MERCHANTABILITY, WARRANTY OF FITNESS FOR A PARTICULAR PURPOSE OR ANY IMPLIED WARRANTY IS MADE. The following warranty is made in lieu of such warranties and all other warranties, express, implied, or statutory. Products are warranted to be free from defects in material and workmanship at the time sold. The sole obligation of seller and manufacturer under this warranty shall be to replace any noncompliant product at the time sold. Under no circumstances shall manufacturer or seller be liable for any loss, damage or expense, direct, indirect, incidental or consequential, arising out of the inability to use the product. Notwithstanding the foregoing, if products are supplied in response to a customer request that specifies operating parameters beyond those stated above, or if products are used under conditions exceeding said parameters, the customer by acceptance or use thereof assumes all risk of product failure and of all direct, indirect, incidental and consequential damages that may result from use of the products under such conditions, and agrees to exonerate, indemnify, defend and hold harmless MacDermid, Incorporated and its affiliates therefrom. No suggestion for product use nor anything contained herein shall be construed as a recommendation to use any product in a manner that infringes any patent or other intellectual property rights, and seller and manufacturer assume no responsibility or liability for any such infringement.

© 2019 MacDermid, Inc. and its group of companies. All rights reserved. "R" and "TM" are registered trademarks of MacDermid, Inc. and its group of companies in the United States and/or other countries.