



Poly and Vinyl Packaging and Specialty Products  
 2399 Silver Wolf Drive ▪ Henderson, NV 89011-4431 USA  
 (702) 565-7500 ▪ FAX (702) 565-3838 ▪ FAX (800) 669-9811  
[www.armandmfg.com](http://www.armandmfg.com) ▪ Email: sales@armandmfg.net

## MATERIAL DATA

### **Static Dissipative Vinyl** Clear Matte Static Dissipative Vinyl .0065

#### Product

Clear Matte Static Dissipative Vinyl .0065

#### Physical Properties

Property	Value
Color	Clear
Finish	Matte
Thickness	.0065 (6.5 mil) Nominal +/- 0.0005 (+/- 0.5 mil)
Hand	H
Characteristics	Static Dissipative Cold Impact at +10°F

Property	Machine Direction	Transverse Direction
Tensile Strength (psi)	3000 min.	2900 min.
Elongation (%)	250 min.	260 min.
100% Modulus (psi)	1700 min.	1500 min.

Test	Test Methods	Average Values
Surface Resistivity	ASTM D257	$10^9$ - $10^{11}$ ohms/sq.
Static Decay	ASTM 101, Method 4046	.06 seconds
Contact Corrosivity	ASTM 101C, Method 3005	none

The values and information provided in this document have been provided directly to Armand from our material supplier.  
 This information is given as an indication of typical values and provided without any obligation on our part.