

# 419D Liquid



## Acrylic Conformal Coating

419D is a 1-part acrylic conformal coating that cures to a durable, flexible and smooth finish. It is easy to apply and can be handled in 10 minutes. It may be removed with appropriate strippers, or soldered through for repair or rework.

419D creates a robust moisture barrier that protects printed circuit boards in humid environments. It protects effectively against moisture, corrosion, fungus, dirt, dust, thermal shock, short circuits, high voltage arcing, and static discharge.



## Features and Benefits

- Certified UL 94 V-0 (File# E203094)
- Certified IPC-CC-830B
- Xylene and toluene free
- Fluoresces under UV-A light
- Suitable for use with selective coating equipment

## Available Packaging

Cat. No.	Packaging	Net Vol.	Net Wt.
419D-55ML	Bottle	55 mL	50.6 g
419D-1L	Can	945 mL	869 g
419D-4L	Can	3.78 L	3.47 kg
419D-20L	Pail	18.9 L	17.3 kg

## Cured Properties

Resistivity	$4.6 \times 10^{14} \Omega \cdot \text{cm}$
Dielectric Strength	1 000 V/mil
Dielectric Withstand Voltage	>1 500 V
Insulation Resistance	$1 \times 10^{13} \Omega$
Moisture Insulation Resistance	$1 \times 10^{12} \Omega$
Dielectric Constant @ 1 MHz	2.85
Dissipation Factor @ 1 MHz	0.004
Glass Transition Temperature ( $T_g$ )	27 °C
CTE Prior $T_g$	72 ppm/°C
Service Temperature Range	-65–125 °C

## Usage Parameters

Dry Time To Handle (1 coat)	10 min
(2 coats)	20 min
Minimum Recoat Time	3 min
Recommended Film Thickness	25–75 $\mu\text{m}$
Theoretical Coverage @ 25 $\mu\text{m}$	94 020 $\text{cm}^2/\text{L}$

## Uncured Properties

Viscosity @ 25 °C	115 cP
Density	0.92 g/mL
Percent Solids	30 %
Shelf Life	5 y
Calculated VOC	654 g/L

# 419D Liquid



## Application Instructions

Read the product SDS before using this product.

## Recommended Preparation

Clean the substrate with Isopropyl Alcohol, MG #824, so the surface is free of oils, dust, and other residues.

## Recommended Thinner

When thinning is required, use MG #4352 Thinner 2.

## Brush

419D can be applied by brush for rework or touch-ups. Thinning is not required for most brush applications. Desired coating thickness can be achieved in a single application. Applied coating can be cured immediately.

## Manual Spray Guns

Use a standard fluid nozzle gun with a minimum tip diameter of 0.8–1.0 mm. The settings listed below are recommendations; however, performance will vary with different brands:

Inlet	Air flow	Air cap
20–40 psi	10–15 SCFM	8–10 psi

1. Dilute 1-part coating to 1-part thinner (MG #4352 Thinner 2). Adjust ratio if required.
2. Stir the coating gently, but thoroughly.
3. Spray a test pattern to ensure good flow quality.
4. Tilt the board at 45° and spray a thin even coat from a distance of 20–25 cm (8–10 in). Use spray-and-release strokes with an even motion to avoid paint buildup in one spot. Start and end each stroke off the surface.
5. Wait 3 min between coats to avoid trapping solvent.
6. Rotate the board 90° and spray again to ensure good coverage.
7. Apply additional coats until desired thickness is achieved (go to step 3).
8. Let dry for 10 min at room temperature before applying heat cure.

## Dip Coat

Use a Ford or Zahn cup to monitor the viscosity of the coating, as the solvent will evaporate over time.

1. Hang the PCB on a dipping arm.

2. Slowly lower the PCB into a tank and leave immersed in the coating for 2 min to allow penetration.
3. Slowly withdraw the PCB from the tank at a rate of approximately 6" per minute.
4. Let dry for 3 min before applying additional coats or 10 min before heat cure.

## Selective Coating

For higher volume applications, coating can be applied via selective coating equipment. The settings listed below are recommendations and performance will vary with different brands.

Settings	PVA	Nordson Asymtek
Platform	PVA 650	SL 940E
Valve	FCS300-ES	SC 280N
Dilution	3:2 with 4352	8:3 with 4352
Air Pressure	0.2 psi	80 psi
Fluid Pressure	10 psi	23 psi
Dispense Height	10 mm	12.7 mm
Pass Width	4 mm	N/Av
Coating Speed	100 mm/sec	381 mm/sec

## Cure Instructions

Allow to dry at room temperature for 24 hours, or after letting sit for 10 minutes, cure the coating in an oven at one of these time/temperature options:

<b>Temperature</b>	65 °C	80 °C	100 °C	120 °C
<b>Time</b>	30 min	20 min	10 min	5 min

## Clean-up

Clean spray system and equipment with MEK or acetone, MG #434.

## Storage and Handling

Store between -5 and 40 °C in a dry area, away from sunlight (see SDS).

## Disclaimer

This information is believed to be accurate. It is intended for professional end-users who have the skills required to evaluate and use the data properly. M.G. Chemicals Ltd. does not guarantee the accuracy of the data and assumes no liability in connection with damages incurred while using it.