
Product: 4300
Dissipative Polyurethane
 Typical Physical Properties

Physical Property	Value	Test Method
Color	Pink	
Density (lbs / ft ³)	1.15-1.35	ASTM D 3574 -01
Indent Force Deflection-@25%	32-38	ASTM D 3574 -01
Compression Set (%)	10	ASTM D 3574 -01
Tensile Strength (psi)	12	ASTM D 3574 -01
Tear Resistance(lbs/inch)	1.2	ASTM D 3574 -01
Elongation(%)	100	ASTM D 3574 -01
Flame Resistance	n/a	MIL-PRF-2651G
Electrostatic Decay (seconds)	2.0	FTMS 101C; Method 4046
Surface Resistivity(Ohms)	10 ¹¹	ASTM D-257

This information is based on actual testing in a controlled environment. However, as conditions of use are not within our control, CCI does not guarantee from use of such products or other information herein; no warranty expressed or implied is given. It is the user's responsibility to determine the appropriateness of the products for their specific end uses.

3/7/07

www.corstat.com